

Sheet Thickness	Grey / Grey GSM	White / Grey GSM	Bending Resistance (Stiffness) MD	Bending Resistance (Stiffness) CD
(mm) +/-0.05	gram / m2 +/- 5%	gram / m2 +/- 5%	mN.M +/- 15%	mN.M +/- 15%
1.0	660	680	710	362
1.1	726	748	845	310
1.2	792	816	1105	505
1.3	858	884	1210	670
1.4	924	952	1325	695
1.5	990	1020	1490	710
1.6	1056	1088	1675	881
1.7	1122	1156	1765	895
1.8	1188	1224	2035	1038
1.9	1254	1292	2185	1190
2.0	1320	1360	2290	1235
2.1	1386	1428	2360	1295
2.2	1452	1496	2455	1320
2.3	1518	1564	2589	1410
2.4	1584	1632	2620	1490
2.5	1650	1700	2750	2155
2.6	1716	1768	2995	2330
2.7	1782	1836	4010	2780
2.8	1848	1904	5285	3230
2.9	1914	1972	5410	3630
3.0	1980	2040	5565	3870

Moisture	0.07	+/- 2%
Flatness	0	0.2% - 1.5 %

